

HAIFLON® PPA 9028T — up to 350 °C

Fluoropolymer-based processing aid for polyolefin extrusion

Haiflon® PPA 9028T is a free-flowing white powder fluoropolymer-based processing aid for polyolefin processing at very low addition levels (50 – 800 ppm), without affecting the original physical properties of the plastics, nor their sealing, adhesion and printing properties. It can be used for mLLDPE, LLDPE, HDPE, LDPE, EVA and other polyolefin resins at extrusion temperatures up to 350 °C.

Product Features

- ✧ Ultra-high-temperature stability — extrusion up to 350 °C
- ✧ Improves pigment dispersion in masterbatch and colored products
- ✧ Improves the processing performance of low-melt-flow resins
- ✧ Improves film surface quality by eliminating melt fracture (sharkskin, orange peel)
- ✧ Reduces die wear and eliminates die buildup, extending continuous production time
- ✧ Increases output and saves energy (lower main motor current)

Typical Physical Properties

Item	Specification — PPA 9028T
Appearance	White to off-white powder
Bulk density, g/cm ³	0.6 – 0.8
Extrusion temperature, °C	up to 350
Particle size, mesh	< 10
Volatile (105 °C, 1 h), %	< 1

Applications

- ✧ Extrusion of LLDPE, HDPE, mLLDPE and other polyolefin resins
- ✧ PP, PC, PET, ABS and other engineering resins
- ✧ High-temperature extrusion processes up to 350 °C

Processing Guide

- ✧ The dispersion of the PPA in the resin determines the performance. The recommended procedure is to make a 2 – 3 % masterbatch through a twin-screw extruder and then dose it into the extrusion resin according to the target performance level. The conditioning time is 20 – 60 minutes depending on equipment, base material and shear rate; no conditioning time is required under long-term continuous use.
- ✧ Typical effective dosage: 50 – 800 ppm.

Shelf Life & Storage

- ✧ 2 years, below 30 °C, stored cool and protected from light.

Food Contact Safety

- ✧ Meets the requirements of FDA 21 CFR 177.1520 (USA) when properly used; suitable for food-contact applications.

Safety Precautions

- ✧ Not classified as a dangerous good for transport. Please refer to the Safety Data Sheet (SDS) before use.
- ✧ Avoid breathing dust; use local exhaust ventilation and wear a dust mask, gloves and goggles during handling.
- ✧ During hot processing above 300 °C, small amounts of decomposition products may be released — adequately ventilate the processing area and avoid inhaling fumes.
- ✧ Dispose of processing waste according to local regulations.

Packing

- ✧ Net weight 25 kg per carton.
- ✧ Other packings are available on request.